

# T5100

## Polypropylene (PP)

### Description:

T5100 is a Random Copolymer Polypropylene with high rigidity, high heat resistance and low melt flow index. It is suitable for using in extrusion process.

### Typical applications;

Extrusion Pipe Process : Hot water pipe application

Physical Properties:	Method	Unit	Value
Density	ASTM D792	g/cm <sup>3</sup>	0.90
Melt Flow Index (2.16 kg/230°C)	ASTM D1238	g/10min.	0.25
Tensile Strength at Yield	ASTM D638	MPa	32
Notched Izod Impact Strength (at 23°C)	ASTM D256	J/m	260
Flexural Modulus (1% SECANT)	ASTM D790	MPa	1050
Heat Distortion Temperature @ 4.6 kg	ASTM D648	°C	85

### Processing Technique

**Processing Temperature : 190 – 240 °C**

\*\*However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.\*\*

**Remark:** The values presented on the above are typical laboratory average, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitability of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.