

HD2228J

High Density Polyethylene Resin

Special Characteristics

InnoPlus HD2228J is high density polyethylene injection molding grade. They are tailored with very narrow molecular weight distribution (MWD) result for good impact strength and better processability. Furthermore, they are UV stabilizer added that give the excellent UV resistance for outdoor applications such as auto part and industrial product.

Typical Application : Crates, Pallets, Garbage bins, Fruit baskets and Container lids

Typical Properties :

Properties	Value	Unit	Test Method
<i><u>Physical Properties</u></i>			
Melt Flow Rate (190 °C, 2.16 kg)	4.0	g/10 min	ASTM D1238
Density	0.960	g/cm ³	ASTM D1505
Vicat softening point @ 10 N, 50 °C/hr	127	°C	ASTM D1525
Melting Point	136	°C	ASTM D3418
<i><u>Mechanical Properties(Based on compression specimens)</u></i>			
Tensile Strength @ Yield	300	kg/cm ²	ASTM D638
Tensile Strength @ Break	300	kg/cm ²	ASTM D638
Elongation @ Break	>1000	%	ASTM D638
Stiffness	11000	kg/cm ²	ASTM D747
Flexural Modulus	13000	kg/cm ²	ASTM D790
Notched Izod Impact Strength	6 (P)*	kg.cm/cm	ASTM D256
Durometer Hardness	66	Shore D	ASTM D2240
ESCR, F ₅₀ (Condition B, 25 % Igepal)	6	hrs	ASTM D1693

* P = Partial Break

HD2228J

High Density Polyethylene Resin

Processing Condition :

Injection Molding temperature : 190 - 230 °C

FDA Statement :

HDPE under the brand InnoPlus complies with U.S. FDA 21 CFR 177.1520 (c) (2.1) and (2.2) regulation for polyethylene used in articles that contact food suitable for articles used for packaging or holding food during cooking.

Disclaimer :

This Applications specified herein is for reference only and not suitable for using in the manufacturing of any products in medical and pharmaceutical sectors.

- Determination of suitability of the product for the use and purpose shall be the customer's responsibility. Customer is obligated to inspect and test the product for such suitability. Customer is responsible for appropriate, safe, legal use processing and handling of the product.
- To our best knowledge, information contained herein is true and accurate as of the date of its publication. However, we make no representations or warranties with respect to accuracy, reliability and completeness of the information contained herein for any purpose.
- No warranties, express or implied, which extend beyond the description herein are given by us. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- We assume no liability for any use of the product in combination with other materials. The information contained herein entirely relates to the product when it is not used in combination with any third party's materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.