

LL5420A

Linear Low Density Polyethylene Resin

Special Characteristics : InnoPlus LL5420A resin is a linear low density polyethylene which is designed for cap and closure application. This grade has high melt flow rate for excellent processability with short cycle time and high productivity, offers an outstanding impact resistance and hinge properties with organoleptic testing passed.

Typical Applications: InnoPlus LL5420A is recommended for producing cap and closure applications; edible oil cap, seasoning source cap, water gallon cap and lid.

Typical Properties:

Properties	LL5420A	Unit	Test Method
Physical Properties			
Melt Flow Rate (190 °C, 2.16 kg)	20	g/10 min	ASTM D1238
Density	0.924	g/cm ³	ASTM D792
Melting Temperature	123	°C	ASTM D3418
Vicat softening point	92	°C	ASTM D1525
Mechanical Properties			
Tensile Strength at Yield	15	MPa	ASTM D638
Tensile Strength at Break	10	MPa	ASTM D638
Elongation at Break	700	%	ASTM D638
Durometer Hardness	53	Shore D	ASTM D2240
Flexural Modulus	370	MPa	ASTM D790
1% Secant Modulus	310	MPa	ASTM D638
Notched Izod Impact Strength	58	Kg.cm/cm	ASTM D256
ESCR, F50 (Condition B, 10 % Igepal)	4	hrs	ASTM D1693

Recommendation:

The recommended temperature setting is in the range of 170 – 190 °C for extruder and 180 – 200 °C for Nozzle.

FDA Statement:

Food and Drug Administration US FDA 21 CFR 177.1520 and Commission Regulation (EU) 10/2011. More compliance regulations and standards that related to the product shall be exhibited in Product Regulatory Certificate (PRC) document.

Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.