

# LL6420A

Linear Low Density Polyethylene Resin

**Special Characteristics :** InnoPlus LL6420A resin is a linear low density polyethylene with butene comonomers, without slip and antiblock designed for extrusion process for wire and cable applications.

**Typical Applications:** This grade is suitable for one-step or two-step silane crosslinkable insulation process for Low voltage power cable insulation, Low voltage telecommunication and Low voltage power cable jacketing.

**Typical Properties:**

Properties	LL6420A	Unit	Test Method
<b>Physical Properties</b>			
Melt Flow Rate (190 °C, 2.16 kg)	2.0	g/10 min	ASTM D1238
Density	0.918	g/cm <sup>3</sup>	ASTM D792
Melting Temperature	120	°C	ASTM D3418
Vicat softening point	97	°C	ASTM D1525
<b>Mechanical Properties (Based on compression specimens)</b>			
Tensile Strength at Yield	10	MPa	ASTM D638
Tensile Strength at Break	25	MPa	ASTM D638
Elongation at Break	900	%	ASTM D638
Secant Modulus	200	MPa	ASTM D638
Durometer Hardness	47	Shore D	ASTM D2240
<b>Electrical Properties</b>			
Volume Resistivity (500V)	2x10 <sup>15</sup>	Ohm.cm	ASTM D257
Dielectric Strength (500V/sec)	25	kV/mm	ASTM D149
Dielectric Constant (60 Hz)	2.2	-	ASTM D150
Dissipation Factor (60 Hz)	0.003	-	ASTM D150

**Recommendation:**

The recommended temperature setting is in the range of 160 – 180 °C for extruder and 170 – 190 °C for die zone.

**Disclaimer:** To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.