

# LL7410D1

Linear Low Density Polyethylene Resin

**Special Characteristics :** InnoPlus LL7410D1 resin is a linear low density polyethylene with butene comonomers, with low content of slip and antiblock. This grade offers the excellent machinability on conversion lines. Films extruded from InnoPlus LL7410D1 have high tensile strength, elongation, good toughness and outstanding puncture strength. It is available for tubular blown film processing.

**Typical Applications :** InnoPlus LL7410D1 is recommended for producing the general purpose films, liners, food packaging, heavy duty and agricultural films.

**Additives :** Slip 700 ppm and Antiblock 700 ppm

**Typical Properties :**

Properties	LL7410D1	Unit	Test Method
<b>Physical Properties (Based on pellets and press-molded sheet)</b>			
Melt Flow Rate (190 °C, 2.16 kg)	1.0	g/10 min	ASTM D1238
Density	0.920	g/cm <sup>3</sup>	ASTM D792
Melting Temperature	121	°C	ASTM D3418
Vicat softening point	101	°C	ASTM D1525

## Film Properties\* (Based on blown film)

Tensile Strength at Break (MD/TD)	34 / 26	MPa	ASTM D882
Elongation at Break (MD/TD)	600 / 800	%	ASTM D882
Tensile Modulus, 1% Secant (MD/TD)	190 / 230	MPa	ASTM D882
Dart Impact Strength	90	g	ASTM D1709
Tear Strength (MD/TD)	100 / 300	g	ASTM D1922
Haze	13	%	ASTM D1003
Gloss (45°)	50	-	ASTM D2457

\* Film made on blown film line at blow up ratio 2.5. Gloss (45°) obtained from 40 microns film while other film properties obtained from 25 microns film.

### Recommendation :

The recommended temperature setting is in the range of 160 – 180 °C for extruder and 170 – 190 °C for die zone.

### FDA Statement :

Food and Drug Administration US FDA 21 CFR 177.1520 and Commission Regulation (EU) 10/2011. More compliance regulations and standards that related to the product shall be exhibited in Product Regulatory Certificate (PRC) document.

**Disclaimer:** To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

*Note :* Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.