

LL7625A

Linear Low Density Polyethylene Resin

Special Characteristics : InnoPlus LL7625A is a linear low density polyethylene with hexene comonomer, without slip and antiblock. InnoPlus LL7625A have been developed for cast film application by offering the excellent toughness, high mechanical strength and elongation with good process stability for high throughput.

Typical Applications : InnoPlus LL7625A is recommended for cast stretch film and in blending formula for producing food packaging and general purpose films.

Additives : No Slip and No Antiblock

Typical Properties :

Properties	LL7625A		Unit	Test Method
Physical Properties				
Melt Index (190 °C, 2.16 kg)	2.5	2.5	g/10 min	ASTM D1238
Density	0.919	0.919	g/cm ³	ASTM D792
Melting Temperature	121	121	°C	ASTM D3418
Vicat Softening Point	100	100	°C	ASTM D1525

Film Properties	Based on blown film*	Based on cast film**		
Tensile Strength at Break (MD/TD)	52 / 29	30 / 30	MPa	
Elongation at Break (MD/TD)	600 / 680	750 / 800	%	ASTM D882
Tensile Modulus, 1% Secant (MD/TD)	215 / 230	250 / 300	MPa	ASTM D882
Dart Impact Strength	110	120	g	ASTM D882
Tear Strength (MD/TD)	300 / 500	250 / 500	g	ASTM D1709
Haze	2.0	19	%	ASTM D1922
Gloss (45°)	91	20	-	ASTM D1003
				ASTM D2457

* Film made on cast film line. Film properties obtained from 25 microns film.

**Film made on blown film line at blow up ratio 2.5. Gloss (45°) obtained from 40 microns film while other film properties obtained from 25 microns film.

Recommendation :

The recommended temperature setting is in the range of 160 - 180 °C for extruder and 170 - 190 °C for die zone.

FDA Statement :

Food and Drug Administration US FDA 21 CFR 177.1520 and Commission Regulation (EU) 10/2011. More compliance regulations and standards that related to the product shall be exhibited in Product Regulatory Certificate (PRC) document.

Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note: Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.