

# 1100PK

## Polypropylene (PP)

### Description:

1100PK is a Polypropylene Homo-polymer with the characteristic of high flow, good stiffness and good process ability for injection molding and multi-filament process. It is suitable for the complex part, long path and thin wall. It also meets the F.D.A. requirement in the code of federal regulations in 21 CFR 177.1520 for food contact.

### Typical applications:

Injection Molding : house-ware, thin wall product, food container and etc.  
Multi-filament : belt, fiber for carpet and etc.

Physical Properties:	Method	Unit	Value
Melt Flow Index (2.16 kg/230°C)	ASTM D1238	g/10min.	15
Tensile Strength at Yield	ASTM D638	N/mm <sup>2</sup>	36
Elongation at Yield	ASTM D638	%	26
Charpy Notched Impact Strength (at 23°C)	DIN 53453	mJ/mm <sup>2</sup>	2.5
Flexural Modulus (1% SECANT)	ASTM D790	MPa	1500
Rockwell Hardness	ASTM D785	R-Scale	107
Heat Distortion Temperature (Load 0.45 N/MM <sup>2</sup> )	ASTM D 648	°C	110

### Processing Technique

**Processing Temperature : 200 – 240 °C**

\*\*However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.\*\*

**Remark:** The values presented on the above are typical laboratory average, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitability of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.