

UV1070 Physical Properties

Applications :	Shoes, Ink and solvent base Adhesive formulation	Regulatory information
Characteristics :	Polarity and high solubility	Complied with the RoHS Directive 2011/65/EU Annex II [amended by Directive (EU) 2015/863] # (IEC method) For plastics
Additives :	No slip, No Antiblock With thermal stabilizer	Remarks : The values presented in this document are typical laboratory average, not to be construed as specification and may
Process Temp. :	130-180 °C	vary within moderate ranges. The application or accuracy of this information or suitable of our products cannot be guaranteed because the conditions of uses on the part of our users are beyond our control.

Properties	Test Method	Unit	Typical Value
Melt Flow Index (2.16 kg / 190°C)	ASTM D1238	g/10 minutes	50-60
VA Content	TPIPL Method	%	>40
Density	ASTM D1505	g/cm ³	0.963
Vicat Softening Temperature	ASTM D1525	°C	<40
Melting Temperature	ASTM D638	°C	50
Tensile Strength at Break	ASTM D638	МРа	7
Ultimate Elongation	ASTM D638	%	1,000
Hardness Shore A	DIN 53505	-	52

- Page 17 -

TPI Polene Public Company Limited

26/56 TPI Tower 8th floor, Chantadmai Road, Tungmahamek, Sathorn, Bangkok 10120 Thailand. Tel. +66 2285 5090 ext.12072 Fax. +66 2678 7080 Email ldpe_tpipl@hotmail.com