



Thai PET Resin Co., Ltd.

Head Office: 555/1 Energy Complex, Building A, 15th Floor, Vibhavadi Rangsit Road, Chatuchak, Bangkok 10900, Thailand

Tel: +66-2265-8400

Fax: +66-2140-8704

SPECIFICATIONS OF SE030T
Polyethylene Terephthalate Polymer (PET)

Items	Units	Standard	Methods
Intrinsic Viscosity	dl/g	0.80 ± 0.05	MCI Method
Acetaldehyde	ppm	1 max.	MCI Method
Color-L	-	75 min.	MCI Method
Color-b	-	1.0 max.	MCI Method
Diethylene Glycol	%wt	1.10-1.60	MCI Method
Powder	ppm	100 max	MCI Method
Appearance	-	Conformity	MCI Method
Foreign Matters in chip <0.2 mm	pc/100g	5 max	MCI Method
Foreign Matters in chip ≥0.2 mm	pc/100g	0 max	MCI Method
Metallic Foreign Matters	pc/100g	0 max	MCI Method
Moisture	ppm	2000 max	ZIMMER Method
Melting Point	°C	245-249	ASTM D3418

Description

SE030T is a high intrinsic viscosity copolymer resin which is suitably designed for sheet applications. For food applications, the resin is considered safe based upon compliance with the United States Food and Drug Administration. The specialty resin offers good gas-barrier properties, and is tasteless and odorless, with high flavor retention and minimal flavor adsorption.

Warranty

Thai PET Resin warrants that its products will comply with the specifications and related regulatory compliance detailed in its publications. No other warranty, either expressed or implied regarding the suitability of the product for any particular purpose is made. The buyers are expected to make their own determination about the safety, health, environmental protection and suitability of use for their intended purposes. No warranty is made of the merchantability or fitness of any product and nothing herein waives any of the seller's conditions of sale.