

1100XC

Polypropylene Homopolymer (PP) / Meltblown Nonwoven

PRODUCT DESCRIPTION

1100XC is a new series of Polypropylene Homopolymer (PP) producing from non-phthalate catalyst system with characteristics of Very high flow, narrow molecular weight distribution and low volatile content. It is especially designed for multilayer meltblown and spunbond nonwoven using for hygiene and medical application with qualified gas fading resistance.

INDUSTRY

- Hygiene Nonwovens
- Diaper, Sanitary Napkin
- Healthcare Nonwoven
- Medical Clothes
- Absorption & Filtration

PRODUCT FEATURE

- Non-phthalate Catalyst System
- Very High Flow Ability
- Low Volatile Content
- Narrow MWD
- Gas Fading Resistance

REGULATION COMPLIANCE

- FDA US 21 CFR 177.1520
- Commission Regulation (EU) No. 10/2011
- RoHS Directive 2011/65/EU
- REACH Regulation (EC) No. 1907/2006
- US Model Toxics in Packaging Legislation (TPCH) - Phthalates content

PHYSICAL PROPERTY	TEST METHOD	UNIT	VALUE
Melt Flow Rate (230°C/2.16 kg)	ASTM D1238	g/10 min	800
THERMAL PROPERTY			
Volatile Content (105°C, 10 min)	EN 12099	ppm	<500

Conversion (1 MPa = 10.2 kgf/cm² | 1 J/m = 0.1 kgf-cm/cm)

Remark: The values presented above are typical laboratory, not to be construed as specifications and may vary within moderate ranges. The applicability or accuracy of this information or the suitability of our products cannot be guaranteed because users' conditions of use are beyond our control.

1100XC

Polypropylene Homopolymer (PP) / Meltblown Nonwoven

PROCESSING TECHNIQUE

Cylinder Temperature 180 - 260 °C

However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.

PRODUCT PACKAGING

- 20 kg loose bag
- 20 kg stretch wrap on palletized
- 700 kg jumbo bag

For further information, contact IRPC's Sales representative.

STORAGE

The resin should be stored in a dry location with good housekeeping practices during storage, transferring and handling. Process enclosures and adequate ventilation should be used to avoid excessive dust accumulation. Resin should be protected from direct sunlight, temperatures above 38°C (100°F) and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time. The container should be kept closed to prevent contamination. For the additional recommended storage conditions, please refer to SDS.

SAFETY

This product is not classified as hazardous material for more information please refer to safety data sheet.

RECYCLING

It is an undisputed fact that the product can be recycled or disposed of without any problem.

DISCLAIMER

The data indicated above are the results of our investigations, knowledge and correspond to the state of the art as of the date of publication and the data refer to the state of the laws at the date of issue and this information expires after a break in delivery lasting more than 12 months or in case of regulatory changes. This statement is not intended and should not be construed as specification, warranty or representation of any sort for which IRPC would be legal responsibility. The applicability or the accuracy of this statement or the suitability of our products cannot be guaranteed because the conditions of use on the part our uses are beyond our control. IRPC gives no guarantees or makes no warranties which extend beyond the description above herein. Nothing herein shall constitute any implied guaranty or warranty of merchantability or fitness for a particular purpose. In the case that IRPC's products are used in combination with other materials, no liability can be accepted. When not utilized in combination with any third-party products, the information included above refers only to our products. Please ask IRPC for a new information if needed. All terms and conditions regarding the supply of IRPC's products shall be subject to IRPC's Policy, in the case of a dispute, the Company's decision is final and is not subject to any appeal.